



BRILEN POLYESTER INDUSTRIAL YARNS

P.I. Valle del Cinca s/n
22300 Barbastro (Huesca) Spain
Ph.: +34 974 316 065
brilen@samca.com
brilen.com

2025, BRILEN.

All information and material included on this document do not have a contractual nature. Any reproduction, of all or part of this document is expressly prohibited. For the latest version of the data published on this document please refer to our website [brilen.com](https://www.brilen.com).



PORTFOLIO
HIGH TENACITY POLYESTER YARNS



PORTFOLIO HIGH TENACITY POLYESTER YARNS

TECHNICAL DESCRIPTION	TYPE	AVAILABLE TITTLE	FILAMENTS	TENACITY (cN/tex)	ELONGATION (%)	EASF (%)	*SHA (%)
HIGH TENACITY HIGH MODULUS							
HIGH TENACITY AND LOW ELONGATION	GLE	1100-1440-1670-2200-3300-4400-5500-6600-7700-8800-9900	96-192-216-384-576-1152	78-82	12,5	4,5-5,0	8,0
THE LOWEST ELONGATION	FHS	1100-1440-1670-2200-3300	192-384-576	83,0	10,0	4,0	10,5
VERY HIGH STRENGTH	TBF	1100-1250-1670-2200	192-384	86-89	11,5	4,2	9,5
HIGH TENACITY FRICTION RESISTANT	SBX	1100-1670	72-96	78,0	13,5	4,5	8,0
THE HIGHEST TENACITY AND LOW ELONGATION	GLI	1100-1670-2200	192-384	93,0	10,5	3,5	8,0
VERY LOW SHRINKAGE							
VERY LOW SHRINKAGE	VLS	950-1100-1440-1670-2200-3300-4400-5500-6600-7700-9900	192-384-768-576-768-1152	70-72	23-25	13,5-15,0	1,6
ULTRA LOW SHRINKAGE	VLR	1100-1670-2200-3300	192-384-768	71-72	24-26	15,0	1,0
LOW SHRINKAGE LOW ELONGATION	VLP	1100-1670	192-384	74,0	19,5	11,5	1,9
LOW SHRINKAGE HIGH TENACITY	VLT	1100-1670-2200	192-384	76,0	21	12,0	1,6
SUPER ULTRA LOW SHRINKAGE	VLI	1100-1670-2200	192-384	70,0	25	14	0,6
SUPER ULTRA LOW SHRINKAGE HIGH TENACITY	VLD	1100-2200	192-384	82,5	19,5	11,6	1,2
MEDIUM SHRINKAGE							
MEDIUM SHRINKAGE HIGH TENACITY	NLS	1100-1440-1670-2200-3300-4400	192-384-576	76-78	13,0	6,0	4,7
LOWER SHRINKAGE MEDIUM TENACITY	NLR	1100-2200-3300-4400	192-384-768	77,0	19,0	9,0	2,5
MEDIUM SHRINKAGE THE HIGHEST TENACITY	NLI	1100-2200	192-384	90,0	13	5,5	5,0
VERY HIGH SHRINKAGE							
HIGH SHRINKAGE AND HIGH TENACITY	GLS	880-1100-1440	96-192	81,0	12,0	4,2	10,0
HIGH SHRINKAGE AND LOW ELONGATION	GLR	825-880	192	72,0	15,0	4,5	13,0
THE HIGHEST SHRINKAGE	HSF	1100-2200	192-384	79,0	11,0	4,5	14,5
FINE DECITEX							
HIGH TENACITY AND LOW ELONGATION	GLE	140-150-180-190-220-226-330-450-550	24-48-96	80,0	13,0	5,0	8,0
HIGH SHRINKAGE AND HIGH TENACITY	GLS	280-450-550	24-48-96	80,0	12,0	4,5	10,0
HIGH SHRINKAGE AND LOW ELONGATION	GLR	280-330-550	48-96	72,0	14,0	6,0	9,0
THE HIGHEST SHRINKAGE	HSF	220-280-330-450-550	24-48-96	76,0	12,5	4,5	14,0
VERY HIGH STRENGTH	TBF	280	24-48	88,0	11,0	4,0	10,0
MEDIUM SHRINKAGE HIGH TENACITY	NLS	220-280-450-550	24-48-96	78,0	14,5	6,0	5,5
LOWER SHRINKAGE MEDIUM TENACITY	NLR	220-280-550	24-48-96	76,0	19,0	9,0	2,5
VERY LOW SHRINKAGE	VLS	140-167-220-280-330-440-450-550-660	24-48-96	70,0-71,0	21,0-23,0	13,5	1,6-2,0
ULTRA LOW SHRINKAGE	VLR	140-280-330-550	24-48-96	72,0	23,0	14,0	1,1

All the types of this list could be also available in customized decitex/filaments, and special properties could be achieved, based on projects with customers.

*SHA analysed with LENZING (180°, 2 min and pretension: 0.5 cN/tex; except for VERY LOW SHRINKAGE: pretension 0.1 cN/tex). **These are orientative values and could vary depending on decitex and filament number.

ADDITIONAL PROPERTIES available in all types

SPUN DYED YARNS | R-PET YARNS | FLAME RETARDANT YARNS | FOOD CONTACT | WATER APPROVAL | LOW-WICK YARNS

SPECIALTIES, project based

DST-DEEP SEA TREATMENT | UV RESISTANT YARNS | BIODEGRADABLE YARNS | POLYPROPYLENE | POLYAMIDE 6

Please, ask our commercial team to find the best solution for you (brilenht@samca.com)