

VERY HIGH SHRINKAGE



GLS - HIGHEST TENACITY

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
GLS	280/48 420/96; 450/96; 550/96; 1100/96 825/192; 880/192 1100/192; 1440/192	80,0	11,5-12,5	4,0-4,2	10,0

GLR - HIGHEST ELONGATION

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
GLR	330/48 420/96; 550/96 830/192; 880/192	72,0	15,0	6,0	9,0

HSF - HIGHEST SHRINKAGE

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
HSF	220/48; 280/48; 330/48 550/96 1100/192; 1440/192 2200/384	72,0-78,5	10,5-12,5	4,5	14,5

*SHA analysed with LENZING (180°, 2 min and pretension 0,5 cN/tex)

FOOD CONTACT VERSION IS AVAILABLE

All our titer portfolio could accomplish FDA 21 CFR 177,2800 (textile and fibers) and Plastics Regulation (Framework Regulation No 1935/2004 and Regulation No 10/2011).

Any special request on properties, spool format or certification could be available under request. Please, contact our commercial team.