

VERY LOW SHRINKAGE



VLS - VERY LOW SHRINKAGE

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA (%)
VLS	660/96 825/192; 880/192; 950/192; 1100/192; 1440/192; 1670/192 2200/384; 2880/384; 3300/384; 4400/384 5500/768; 6600/768; 7700/768	70-72	23-26	14	1,6

VLR - ULTRA LOW SHRINKAGE

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
VLR	1100/192; 1670/192 1670/384; 2200/384 3300/768	68-71	26	16	1,0

VLD - HIGHEST TENACITY LOWEST SHRINKAGE

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
VLD	1100/192; 2200/384	81	19,5	11,5	12

VLP - LOWEST ELONGATION

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
VLP	1100/192; 1670/384	76-77	19,5	11,5	1,9

VLT - HIGHEST TENACITY

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
VLT	1100/192; 1670/384	76	21	13	1,7

VLI - DIMENSIONAL STABILITY

Type	Titer/Filaments	Tenacity (cN/tex)	Elongation (%)	EASF (%)	SHA* (%)
VLI	1100/192 1670/384; 2200/384	70	25	16	0,6

*SHA analysed with LENZING (180°, 2 min and pretension: 0,1 cN/tex)

LOW-WICK VERSION IS AVAILABLE

FOOD CONTACT VERSION IS AVAILABLE

All our titer portfolio could accomplish FDA 21 CFR 177,2800 (textile and fibers) and Plastics Regulation (Framework Regulation No 1935/2004 and Regulation No 10/2011).

Any special request on properties, spool format or certification could be available under request. Please, contact our commercial team.